



FIG. 9.15 Coil sample holder for measuring the effect of strain on the critical current of long superconductor samples (from Walters et al. 1986). The sample is soldered to a spring, which is twisted and untwisted through small angles to apply axial strain to the superconductor. Sample strain is measured by the angle of rotation of the coil.